

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 July 2002 (18.07.2002)

PCT

(10) International Publication Number
WO 02/055181 A1

(51) International Patent Classification⁷: **B01D 53/94**,
B01J 23/58, 37/02, F01N 3/08

(74) Agents: **CIHOSZ, Vincent, A.**; Delphi Technologies,
Inc., Legal Staff MC 480-414-420, P.O. Box 5052, Troy,
MI 48007-5052 et al. (US).

(21) International Application Number: PCT/US01/02840

(81) Designated State (national): JP.

(22) International Filing Date: 29 January 2001 (29.01.2001)

(84) Designated States (regional): European patent (AT, BE,
CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC,
NL, PT, SE, TR).

(25) Filing Language: English

(26) Publication Language: English

Published:

with international search report


(30) Priority Data:
09/758,948 11 January 2001 (11.01.2001) US

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(71) Applicant: **DELPHI TECHNOLOGIES, INC.**
[US/US]; Legal Staff MC 480-414-420, 1450 West
Long Lake Road, Troy, MI 48007-5052 (US).

(72) Inventors: **DOU, Danan**; 9301 S. 87th East Avenue,
Catoosa, OK 74015 (US). **BAILEY, Owen**; 22415 S. Rose
Glen Court, Claremore, OK 74017 (US).

(54) Title: METHODS TO REDUCE ALKALI MATERIAL MIGRATION FROM NO_x ADSORBER WASHCOAT TO
CORDIERITE



K scavenger in barrier

(57) Abstract: An exhaust gas catalyst system, comprising: a substrate; and a nitrogen oxides adsorber deposited on said substrate, the nitrogen oxides adsorber comprising: a porous support; and a material loaded on said porous support comprising: a NO oxidation catalyst, at least one alkali material, and at least one alkali metal barrier. An exhaust gas catalyst system, comprising: a substrate; an alkali metal barrier layer deposited on said substrate; and a nitrogen oxides adsorber deposited on said alkali metal barrier layer, the nitrogen oxides adsorber comprising: a porous support; and a material loaded on said porous support comprising a NO oxidation catalyst and at least one alkali material. A method of reducing alkali material migration from a nitrogen oxides adsorber washcoat to a substrate, comprising: depositing on a substrate, an alkali metal barrier layer; and depositing on said alkali metal barrier layer, a nitrogen oxides adsorber comprising a material loaded on a porous support, the material comprising a NO oxidation catalyst and at least one alkali material. A method of reducing alkali material migration from a nitrogen oxides adsorber washcoat to a substrate, comprising: depositing on a substrate, a nitrogen oxides adsorber composition comprising a material loaded on a porous support, the material comprising a NO_x oxidation catalyst, at least one alkali material, and at least one alkali metal barrier.

WO 02/055181 A1

METHODS TO REDUCE ALKALI MATERIAL MIGRATION FROM NO_x ADSORBER WASHCOAT TO CORDIERITE

CROSS REFERENCE TO RELATED APPLICATIONS

This application claims the benefit of the filing date of U.S. Provisional Application Serial No. 09/483,639 filed on January 14, 2000, which is hereby incorporated by reference.

TECHNICAL FIELD

The present disclosure relates to nitrogen oxide adsorption materials used in exhaust systems of internal combustion engines.

BACKGROUND

It is well known in the art to use catalyst compositions, including those commonly referred to as three-way conversion catalysts ("TWC catalysts") to treat the exhaust gases of internal combustion engines. Such catalysts, containing precious metals like platinum, palladium, and rhodium, have been found both to successfully promote the oxidation of unburned hydrocarbons (HC) and carbon monoxide (CO) and to promote the reduction of nitrogen oxides (NO_x) in exhaust gas, provided that the engine is operated with an air/fuel ratio of nearly balanced stoichiometry for combustion ("combustion stoichiometry") (i.e., between about 14.7 and about 14.4) on a mass basis.

To realize a benefit in fuel economy and reduce global CO₂ emissions it is desirable to operate the engine under lean-burn conditions, where the air-to-fuel ratio is somewhat greater than stoichiometric (i.e., greater than about 14.7 and generally between about 19 and about 55). When lean-burn conditions are employed, three-way catalysts are efficient in oxidizing the unburned hydrocarbons and carbon monoxide, but are inefficient in the reduction of nitrogen oxides.

In order to improve nitrogen oxide reduction under lean-burn conditions, artisans have employed NO_x adsorbers in combination with the three-way catalysts. In the adsorber, catalytic material acts first to oxidize NO_x to NO₂. NO₂ then reacts with the alkali and alkaline earth materials to form
5 stable nitrate salts. In a gas mixture corresponding to stoichiometric combustion or a fuel rich environment, the nitrate is thermodynamically unstable, and the stored NO_x is released for catalysis, whereupon NO_x is reduced to N₂ gas.

These NO_x adsorbers generally comprise a catalytic metal, such as platinum, palladium, and/or rhodium, in combination with an alkali and/or
10 alkaline earth element (e.g., barium (Ba), strontium (Sr), calcium (Ca), magnesium (Mg), and the like, as well as combinations comprising at least one of the foregoing), (hereinafter the "alkali material") loaded on a washcoat. The washcoat, which is a porous support material suitable for use in high temperature environments, typically comprises high surface area materials like
15 alumina, gamma-alumina, zirconia, cerium oxide (ceria), stabilized cerium oxide and magnesium oxide, among others.

For practical incorporation of the washcoat materials and the catalytic materials into internal combustion engine exhaust systems, the washcoat is, itself, deposited on a chemically stable and/or thermally insulating
20 substrate material. Particularly useful washcoat substrate materials, include cordierite, mullite, metallic materials among others. These substrates are typically in the form of monolithic honeycomb structures, layered materials, or spun fibers, among other configurations.

U.S. Patent No. 5,727,385 to Hepburn, which is herein
25 incorporated by reference, discloses a NO_x trap, comprising; (i) at least one precious metal, selected from platinum and palladium, loaded on a porous support; and (ii) at least one alkali or alkaline earth metal (a) loaded on a porous support or (b) present as an oxide thereof. Hepburn optionally includes a three-

way catalyst located either between the two components or after the NO_x trap material.

The alkali materials, including potassium and sodium, are employed conventionally in NO_x adsorbers because they function as NO_x trapping components. However, they are mobile at high temperatures, particularly in the presence of steam. Thus, potassium and sodium, which are initially present on the NO_x adsorber catalyst washcoat, migrate away from the adsorber catalyst washcoat and into the supporting substrate.

This migration can be clearly seen with reference to Figures 2 and 3 by comparison with Figure 1. Figure 1 shows the typical potassium (K) washcoat concentrations for a NO_x adsorber catalyst washcoat relative to the monolith substrate material. Figure 2 shows the migration of potassium away from the washcoat into the monolith on aging of the NO_x adsorber catalyst in a 900 °C oven with air/H₂O for 16 hours. Figure 3 shows the migration of potassium away from the washcoat on aging of the NO_x adsorber catalyst in engine exhaust at 750 °C for 40 hours. Consequently, substantial migration of potassium occurs at the adsorber catalyst on aging under typical operational conditions.

Table 1 further defines the temperature effects on the migration of potassium from the adsorber washcoat to the substrate. Table 1 establishes the relative distributions of potassium on the catalyst washcoat and on the substrate as a function of the temperature of hydrothermal aging as analyzed by an electron microprobe.

TABLE 1

Hydrothermal aging Temperature (°C)	% K remaining on washcoat	% K migration to substrate
No aging (Fresh)	99	1
600	72	28
700	70	30
800	63	37
900	42	58
1000	30	70

As indicated by Table 1, higher temperature promotes more aggressive migration of potassium away from the active washcoat, thus reducing the NO_x adsorptive properties of the washcoat materials.

Deleterious effects of alkali material migration further include an increase in the elastic modulus (stiffness) and a change in the substrate coefficient of thermal expansion (CTE), both caused by the chemical reaction of the alkali materials with the substrate material. The effect of the changed coefficient of thermal expansion and increased elastic modulus is to make the cordierite or other substrate, and consequently the catalyst, more susceptible to thermal cracking during changes in temperature, especially during rapid temperature changes. For additional information, reference is made to SAE publication number 99013500, *Mechanical Durability of Cordierite-Based NO_x Adsorber/Catalyst Systems for Lean-Burn Gasoline Applications*, by Day, Jay Paul and Cutler, Willard.

What is needed in the art is a NO_x adsorber having improved mechanical durability particularly over high thermal transient.

SUMMARY

The above-described and other disadvantages of the prior art are overcome by the exhaust gas catalyst system and the method of reducing alkali material migration. The system comprises: a substrate and a nitrogen oxide adsorber deposited on said substrate. The nitrogen oxide adsorber comprises a porous support and a material loaded on the porous support. The porous support comprises: a NO oxidation catalyst; at least one alkali material; and at least one alkali metal barrier.

Alternatively, the system comprises a substrate, an alkali metal barrier layer deposited on the substrate, and a nitrogen oxide adsorber deposited on the alkali metal barrier layer. The nitrogen oxide adsorber comprises a porous support and a material loaded on the porous support comprising a NO oxidation catalyst and at least one alkali material.

The method of reducing alkali material migration comprises: depositing an alkali metal barrier layer and a nitrogen oxide adsorber composition on a substrate. The nitrogen oxide adsorber comprises a material loaded on a porous support, with the material comprising a NO oxidation catalyst and at least one alkali material.

Alternatively, The method of reducing alkali material migration comprises depositing a nitrogen oxide adsorber composition on a substrate. The composition comprises a material loaded on a porous support, with the material comprising: a NO oxidation catalyst, at least one alkali material, and at least one alkali metal barrier.

BRIEF DESCRIPTION OF THE DRAWINGS

Referring now to the drawings, which are meant to be exemplary, not limiting, and wherein like elements are numbered alike in several Figures.

Figure 1 shows the typical potassium concentrations for a NO_x adsorber catalyst washcoat relative to the monolith substrate materials.

5 Figure 2 shows the migration of potassium away from the washcoat into the monolith on aging of the NO_x adsorber catalyst in a 900 °C oven with air/H₂O for 16 hours.

 Figure 3 shows the migration of potassium away from the washcoat on aging of the NO_x adsorber catalyst in engine exhaust at 750 °C for
10 40 hours.

 Figure 4 shows an exemplary loading strategy, whereby alkali metal barrier is loaded uniformly into the washcoat material.

 Figure 5 shows an alternate exemplary loading strategy, whereby alkali metal barrier is formed as a layer between the washcoat materials and the
15 monolith substrate.

 Figure 6 is a graphical representation showing the migration of alkali materials on a prior art NO_x adsorber, aged at 900 °C for 16 hours in air and water.

 Figure 7 is a graphical representation showing prevented
20 migration of alkali materials on a NO_x adsorber, using the barrier coating embodiment, aged at 900 °C for 16 hours in air and water.



 Figure 8 is a graphical representation showing the potassium migration for a material with no barrier coating.

Figure 9 is a graphical representation showing the potassium migration for a material with a barrier coating.

DESCRIPTION OF THE PREFERRED EMBODIMENT

The NO_x absorber washcoat (NO_x washcoat) inhibits alkali material migration into the supporting substrate. The NO_x washcoat comprises a NO oxidation catalyst, at least one alkali material, and at least one alkali metal barrier. This NO_x washcoat is preferably loaded onto a porous support, and deposited on a supporting substrate, such as ceramic. During use, the washcoat prevents thermodynamically driven migration of alkali materials into the supporting substrate. Preferably, the NO_x washcoat establishes a barrier preventing alkali material migration out of the porous support.

Alkali material migration occurs principally because alkali materials become mobile when subjected to steam and elevated temperatures. The mobile alkali materials (e.g., sodium (Na), potassium (K), cesium (Cs), rubidium (Rb), lithium (Li), among others and mixtures comprising at least one of the foregoing) which are attracted to the silica (SiO₂) commonly found in the supporting substrate, react with the silica to form stable silicates. Exemplary reactions include:



These reactions support the fact that once alkali materials are mobile, migration of alkali materials, specifically sodium and potassium, into the silica component of a ceramic substrate is driven even at operating temperatures expected for NO_x adsorber applications.

In order to inhibit migration of the alkali materials into the supporting substrate and preferably to prevent migration out of the NO_x washcoat, an alkali metal barrier is incorporated into the washcoat and/or employed as a barrier between the washcoat and the supporting substrate.

5 Possible alkali metal barrier, which trap and/or block alkali material migration into the supporting substrate include alkali metal barriers, preferably early transition metal oxides, and more preferably zirconia (ZrO₂), titania (TiO₂), ferric oxide (Fe₂O₃), silica (SiO₂), cordierite, mullite, tin oxide (SnO₂), ceria (CeO₂), manganese oxide (MnO₂), vanadium oxide (V₂O₅),
10 chromium oxide (Cr₂O₃), hafnium oxide (HfO₂), molybdenum oxide (MoO₃), tungsten oxide (WO₃), alpha-alumina, and the like, and mixtures including at least one of these oxides. Optionally, these alkali metal barriers can be supported on alumina or another material. Typically, the alkali metal barriers are deposited/dispersed on the alumina by an impregnation process of soluble
15 precursor solutions followed by calcination to transform precursor salt into their oxide forms. Not to be limited by theory, it is believed that inclusion of the alkali metal barrier causes the formation of alkali metal oxide salts within the washcoat, effectively reducing the thermodynamic migration of alkali materials into the substrate.

20 Generally a sufficient amount of alkali metal barrier is employed to substantially inhibit alkali material migration into the supporting substrate. There are no real limits for the amount of alkali metal barrier that can be loaded onto the washcoat. The bounds of the alkali metal barrier concentration range from an upper amount which would substantially adversely affect NO_x catalyst
25 loadings and cost factors, to a lower limit which does not sufficiently inhibit alkali material migration. If the alkali metal barrier is incorporated into the washcoat, preferably the alkali metal barrier concentration will approach or exceed the stoichiometric loadings for the particular alkali metal barrier, alkali materials, and operating conditions. Though there are no upper or lower limits
30 on alkali metal barrier loadings, generally, for most exhaust system nitrogen

oxide applications, the alkali metal barrier loading is preferably up to about 2 grams per cubic inch (g/in^3) or more, with up to about 0.35 g/in^3 particularly preferred, up to about 0.25 g/in^3 more preferred, and about 0.05 g/in^3 to about 0.20 g/in^3 especially preferred.

5 Alternatively, if the alkali metal barrier is employed as a layer between the washcoat and supporting substrate, the alkali metal barrier could comprise a film thickness ranging from an atomic film (i.e., a film whose thickness is in the order of a few atoms thick) sufficiently thick to substantially seal the surface of the supporting substrate up to several microns (μ) thick (e.g.,
10 up to or exceeding about 100μ). The lower limit would be a function of an ability to apply film and the film's ability to block alkali material migration, while the upper limit would relate to the barrier film's effects on the catalyst loading. It should be noted that a combination of a alkali metal barrier layer and alkali metal barrier in the washcoat can be employed.

15 Formation of the washcoat proceeds by any means known in the art, except that one or more alkali metal barriers is added to the washcoat or coated onto the substrate prior to the washcoat. For example U.S. Patent No. 5,727,385 to Hepburn describes a technique whereby a loading of about 0.2 to about 5 weight percent (wt%) of precious metal catalyst, preferably between
20 about 0.5 and about 2 weight percent, is employed, the particular loading selected being based on the support on which it is loaded. Also included is a loading of about 2 to about 30 weight percent catalyst selected from alkali materials, preferably between about 5 and about 15 percent, is employed, again based on the type of support on which it is loaded.

25 Suitable porous support (washcoat) materials include those materials suitable for use in high temperature environments such as those found in exhaust streams (up to and above $1,000^\circ\text{C}$). Such materials comprise high surface area materials like alumina, gamma-alumina, delta-alumina, zeolite, zirconia, theta-alumina, cerium oxide (ceria), magnesium oxide, titania, silica,

and combinations comprising at least one of these materials, among others. Desirably, the support material has a surface area up to or exceeding about 300 square meters per gram (m^2/g).

The washcoat will, itself, be typically carried on a high temperature, insulating material ("supporting substrate"). Particularly useful support materials for washcoats which are stable in high temperatures include ceramics, cordierite and mullite, among others. This supporting substrate, which may be in any known or commonly employed configuration, is typically formed as a monolithic honeycomb structure, layered materials, or spun fibers, among other configurations.

The washcoat, catalytic materials, and alkali metal barrier(s) may be applied to the supporting substrate either as a mixture or sequentially, where the alkali metal barrier(s) is first disposed on/into the supporting substrate and the catalytic materials, alkali materials, and washcoat are then deposited thereon. There are numerous suitable techniques for application of the catalytic materials, alkali materials, and alkali metal barriers to the supporting substrate, including painting, dipping, imbibing, impregnation, and slurry deposition, among others.

Figure 4 shows the former exemplary loading strategy, whereby alkali metal barrier is loaded uniformly into the washcoat material slurry as a mixture and laid down on the monolith structure. Figure 5 shows an alternate exemplary loading strategy, whereby alkali metal barrier is formed as a layer between the washcoat materials and the supporting substrate.

As mentioned above, the mechanics of formation may follow any solution mechanism as is commonly known in the art. For example, the washcoat material can be impregnated with soluble precursors of the catalytic materials, alkali materials, and alkali metal barriers, whereupon the washcoat is dried and calcinated. Impregnation may occur in any order, for example as a

catalyst solution, followed by an alkali metal barrier precursor solution, followed by an alkali solution, or it may occur as a single step.

However, it should be noted that where impregnation occurs in multiple steps, it is generally preferred to apply the alkali solution subsequent to the alkali metal barrier solution to prevent alkali materials from becoming soluble in the aqueous alkali metal barrier precursor solution. Deposition techniques are well known in the art and selection of any number of techniques and materials can be made to suit the particular materials and circumstances.

The following examples are illustrative and not intended as limiting, and the Table is intended to define the mixed oxides A, B, and C utilized in the Examples.

TABLE			
ZrO ₂ /CeO ₂ /La ₂ O ₃ Mixed Oxides			
Mixed Oxide	Zr (wt%)	Ce (wt%)	La (wt%)
A	18.51	61.05	1.7
B	61.88	11.81	1.62
C	45.83	23.447	7.93

EXAMPLES

Example 1. NO_x adsorber catalyst (no barrier coating; see Figure 6)

Washcoat layer #1. 1200.2g of platinum (Pt) nitrate solution (10.05 wt%) was diluted with de-ionized water (H₂O). Then 944.2g of mixed oxide-A was added to the solution and allowed to mix for 1 hour (hr) before adding 8185g of a powder containing 19.1 wt% of Ba on a theta alumina to form a slurry. The slurry pH is adjusted to 6.44 using acetic acid. It was then

milled to suitable particle sizes and coated onto ceramic substrates. Excess slurry was removed by pressurized air or vacuum. The coated catalysts (i.e., coated substrates) were dried and calcined.

- Washcoat layer #2. 517.7g of palladium nitrate solution (10.01 wt% Pd) is diluted with de-ionized H₂O before adding 1572g of a stabilized alumina to form a slurry. After the slurry was mixed for 30 minutes (min), 528g mixed oxide-B was added. The resulting slurry was milled to required particle sizes and coated on the catalysts containing washcoat layered #1. Excess slurry was removed by pressurized air or vacuum, and further dried and calcined.
- Rhodium (Rh) was coated on the catalyst using a post impregnation method followed by calcination. Finally, the potassium acetate solution was applied to the catalyst and the catalyst was calcined.

Example 2. NO_x adsorber catalyst (no barrier coating)

- Washcoat layer #1. 190.6g of platinum nitrate solution (27.84 wt% Pt) is diluted with de-ionized H₂O. 981.7g mixed oxide-C was added to the solution and allowed to mix for 1 hr prior to adding 7062.2g of theta alumina. The resulting slurry was milled to suitable particle size then coated onto ceramic substrates. Excess slurry was removed by pressurized air or vacuum. The coated catalysts were dried and calcined.

- Washcoat layer #2. 134.5 g of platinum nitrate containing (27.84 wt% Pt) is diluted with de-ionized H₂O. 694.2g of mixed oxide-C was added to the solution and allowed to mix for 1 hr which yielded slurry "A". 207.6g palladium (Pd) nitrate(15.48 wt% Pd) was also diluted with de-ionized H₂O. 2776.8g of stabilized alumina was added to the solution and mixed for 30 min to yield slurry "B". The two slurries "A" and "B" were combined and the combined slurry milled to suitable particle sizes and coated on ceramic substrates. Excess slurry was removed by pressurized air or vacuum. The coated catalysts were dried and calcined. Rh was then coated on the catalyst using a post impregnation method followed by another calcination. Finally, Ba

and K were coated with a solution containing Ba and K acetate of proper concentrations and dried and calcined.

Example 3. NO_x adsorber catalyst (No barrier coating)

Washcoat layer #1. 378.2g platinum nitrate solution (26.55 wt% Pt) was diluted with de-ionized H₂O. 1446.3g mixed oxide-C was added to the solution and allowed to mix for 1 hr to yield slurry "C". 469.2g palladium nitrate (14.27wt% Pd) was diluted with de-ionized H₂O. 5013.7g stabilized alumina was added to the solution and mixed for 30 min to yield slurry "D". The two slurries "C" and "D" were combined and milled to suitable particle size then coated on ceramic substrates. Excess slurry was removed by pressurized air or vacuum. The coated catalysts were dried and calcined.

Washcoat layer #2. 227.7g platinum nitrate solution (30.07 wt% Pt) was diluted with de-ionized H₂O. 303.1g rhodium sulfite (5.02 wt% Rh) was added to the solution. Then 3418.4g of stabilized alumina and 986.1g of mixed oxide-C were added to the solution. The resulting slurry was milled to the suitable particle size and coated onto ceramic substrates. Excess slurry was removed by pressurized air or vacuum. Ba and K were applied by post impregnation of a Ba acetate and K acetate solution containing suitable concentrations, followed by calcinations of the impregnated substrates.

Example 4. NO_x adsorber of Example 1 (K trapping oxide in washcoat (WC))

Washcoat layer #1. 649.7g of platinum nitrate solution (13.01 wt% Pt) was diluted with de-ionized H₂O. 663.8g of mixed oxide-A was added and allowed to mix for 1 hr. Then 5576g of powder containing 19.1 wt% of Ba and 175.2g of cordierite powder, was added to the above solution to form a slurry. The slurry pH was adjusted to 6.21 using acetic acid before milling the slurry to proper particle size suitable for catalyst coating. The slurry was then coated onto ceramic substrates with excess slurry removed by pressurized air or vacuum. The coated catalysts are then dried and calcined.

Washcoat layer #2. 223.2 of palladium nitrate solution (15.48 wt% Pd) was diluted with de-ionized H₂O before adding 1041.3g of a stabilized alumina. After the slurry was mixed for 30 min, 347.3g mixed oxide-B and 38.9g cordierite powder were added. The resulting slurry was then milled to a particle size suitable for catalyst coating. The slurry was then coated onto the calcined catalysts containing washcoat layer #1. Excess slurry was removed by pressurized air or vacuum. The coated catalysts were further dried and calcined. Rh was then coated onto the calcined catalyst using a post impregnation method followed by calcination. Finally, the K acetate solution was applied to the catalyst and the catalyst was again calcined.

Example 5. K trapping oxide in WC with increased loading

Washcoat layer #1. 186.35g of platinum nitrate solution (26.55 wt% Pt) was diluted with de-ionized H₂O. 440g of mixed oxide-A was added to the solution and allowed to mix for 1 hr before adding 2816.3g of a powder containing 19.1 wt% of Ba on a theta alumina and 726g of cordierite powder to form a slurry. The slurry pH is adjusted to 6.18 using acetic acid prior to milling the slurry to suitable particle size and coating ceramic substrates therewith. Excess slurry was removed by pressurized air or vacuum. The coated catalysts are then dried and calcined.

Washcoat layer #2. 132.3g of palladium nitrate solution (14.27 wt% Pd) was diluted with de-ionized H₂O before adding 569.0g of a stabilized alumina to form a slurry. After the slurry was mixed for 30 min, 189.7g mixed oxide-B and 132.8g cordierite powder were added. The resulting slurry was then milled to the desired particle size and coated onto the calcined catalysts containing washcoat layer #1. Excess slurry was removed by pressurized air or vacuum. The coated catalysts were further dried and calcined. Rh was coated on the catalyst using a post impregnation method before subsequent calcination. Finally, the K acetate solution was applied to the catalyst. The catalyst was again calcined.

Example 6. K trapping oxide as barrier coating; see Figure 7

Barrier layer: 430.5g cordierite powder and 430.1g of theta alumina powder were added into de-ionized H₂O to form a slurry. The pH of the slurry was adjusted to 4.26 with nitric acid (HNO₃), before milling the slurry to suitable particle sizes and applying it to the ceramic substrate. The substrate is then dried and calcined.

Washcoat layer #1. 348.7g of platinum nitrate solution (27.84 wt%) was diluted with de-ionized H₂O. Then 762.6g of mixed oxide-A was added and allowed to mix for 1 hr. Then 6405.6g of powder containing 19.1 wt% of Ba on a theta alumina was added to the above solution forming a slurry. The slurry pH was adjusted to 6.53 using acetic acid then milled to suitable particle size and coated onto ceramic substrates. Excess slurry was removed by pressurized air or vacuum. The coated catalysts were then dried and calcined.

Washcoat layer #2. 211.4g of palladium nitrate solution (15.48 wt% Pd) was diluted with de-ionized H₂O, then 986.1g of a stabilized alumina is added to form a slurry. After the slurry is mixed for 30 min, 328.7g of mixed oxide-B was added. The resulting slurry was then milled to required particle size and coated on the calcined catalysts containing washcoat layered #1. Excess slurry was removed by pressurized air or vacuum, then coated catalysts were further dried and calcined. Rh was then coated on the catalyst using a post impregnation method followed by calcination. Finally, the K acetate solution was applied to the catalyst then calcined.

Example 7. SiO₂ as barrier coating

Barrier layer: 841.5g SiO₂ powder, 420.2g of theta alumina powder and 226.2g of Al-20 sol (contains 20.8 wt% solid Al₂O₃) were added into de-ionized H₂O then milled to suitable particle sizes. The resulting slurry was applied to the ceramic substrate followed by drying and calcination.

Washcoat layer #1. 220.6g of platinum nitrate solution (30.07 wt% platinum) was diluted with de-ionized H₂O before adding 1227.1g mixed oxide-C and mixing for 1 hr. Subsequently, 6994.7g of theta alumina was added. The resulting slurry was milled to suitable particle size and coated onto ceramic substrates. Excess slurry was removed by pressurized air or vacuum. The coated catalysts were dried and calcined.

Washcoat layer #2. 78.6 g of platinum nitrate containing (30.07 wt% Pt) was diluted with de-ionized H₂O, 438.3g of mixed oxide-C was added to the solution and allowed to mix for 1 hr to yield slurry "A". 142.2g palladium nitrate (14.27 wt% Pd) was diluted with de-ionized H₂O and 1753.1g of stabilized alumina was added to the solution and mixed for 30 min to yield slurry "B". The two slurries "A" and "B" were combined and then milled to suitable particle sizes prior to coating onto washcoat #1 coated ceramic substrates. Excess slurry was removed by pressurized air or vacuum. The coated catalysts were dried and calcined. Rh was then coated on the catalyst using a post impregnation method followed by another catalyst calcination. Finally, Ba and K were coated onto the calcined catalyst using a solution containing Ba and K acetate. The catalyst was again dried and calcined.

Example 8. Cordierite as barrier coating

Barrier layer: 841.5g cordierite powder, 420.7g of theta alumina powder, and 226.2g of Al-20 sol(containing 20.8% Al₂O₃ solid) were added into de-ionized H₂O to form a slurry that was milled. The pH of the slurry was adjusted to 4.14 with HNO₃. The slurry was then applied to the ceramic substrate, and the substrate was dried and calcined.

Washcoat layer #1. 220.6g of platinum nitrate solution (30.07 wt% Pt) was diluted with de-ionized H₂O prior to adding 1227.1g mixed oxide-C and mixing for 1 hr. 6994.7g of theta alumina was then added. The resulting slurry was milled and coated onto ceramic substrates. Excess slurry was

removed by pressurized air or vacuum. The coated catalysts were dried and calcined.

Washcoat layer #2. 78.6 g of platinum nitrate (30.07 wt% Pt) was diluted with de-ionized H₂O. 438.3g of mixed oxide-C was added to the solution and the solution was mixed for 1 hr to yield slurry "A". 142.2g palladium nitrate (14.27 wt% Pd) was diluted with de-ionized H₂O. 1753.1g of stabilized alumina was added to the solution and the solution was mixed for 30 min to yield slurry "B". The two slurries "A" and "B" were combined, milled, and then coated onto ceramic substrates. Excess slurry was removed by pressurized air or vacuum. The coated catalysts were dried and calcined. Rh was then coated on the catalyst using a post impregnation method followed by another calcination. Finally, Ba and K were coated with a solution containing Ba and K acetate of proper concentrations and dried and calcined.

Example 9: No barrier coating (see Figure 8)

Washcoat layer #1. 77.9g of platinum nitrate solution (22.10 wt% Pt) was diluted with de-ionized H₂O. Then 318.7g mixed oxide-C was added to the solution and the solution was mixed for 1 hr. Then 1104.7g of gamma alumina was added and the resulting slurry was milled. 531.1g of Al-20 sol was add to the slurry prior to coating the slurry onto ceramic substrates. Excess slurry was removed by pressurized air or vacuum. The coated catalysts were dried and calcined.

Washcoat layer #2. 68.2 g of platinum nitrate (22.10 wt% Pt) was diluted with de-ionized H₂O. 295.9g of mixed oxide-C was added to the solution and the solution was mixed for 1 hr to yield slurry "A". 64.0g palladium nitrate (14.27 wt% Pd) was diluted with de-ionized H₂O. 1025.8g of stabilized alumina was added to the solution and the solution was mixed for 30 min to yield slurry "B". The two slurries "A" and "B" were combined and the combined slurry was milled prior to adding 493.2g of Al-20 binder to the slurry. The final slurry was coated onto ceramic substrates. Excess slurry was removed

by pressurized air or vacuum. The coated catalysts were dried and calcined. Rh was then coated on the catalyst using a post impregnation method followed by another calcination. Finally, the catalyst was coated with Ba and K, e.g., a solution containing Ba and K acetate, dried and calcined.

5 **Example 10: Cordierite as barrier coating (see Figure 9)**

Barrier layer: 1881.6g cordierite powder, 470.4g of theta alumina powder, and 678.5g of Al-20 sol (containing 20.8% solid Al_2O_3) were added into de-ionized H_2O , and the solution was milled. The pH of the slurry was adjusted to 3.67 with HNO_3 . The resulting slurry was applied to the
10 ceramic substrate that was then dried and calcined. Washcoat layer-1. 65.63g of platinum nitrate solution (23.42 wt% platinum) was diluted with de-ionized H_2O and mixed for 1 hr with 284.5g mixed oxide-C prior to adding 986.3g of stabilized alumina. The resulting slurry was milled before adding 474.2g of Al-20 sol. Ceramic substrates were then coated with the slurry. Excess slurry was
15 removed by pressurized air or vacuum. The coated catalysts were dried and calcined.

Washcoat layer #2. 175.5 g of platinum nitrate containing (23.42 wt% Pt) was diluted with de-ionized H_2O prior to mixing for 1 hr with 760.9g of mixed oxide-C to yield slurry "A". 164.6g palladium nitrate (14.27 wt% Pd)
20 was diluted with de-ionized H_2O prior to mixing for 30 min with 2637g of stabilized alumina to yield slurry "B". The two slurries "A" and "B" were combined and milled prior to adding 1161.2g of Al-20 binder. The final slurry is coated on the coated ceramic substrates. Excess slurry was removed by pressurized air or vacuum. The coated catalysts were dried and calcined prior to
25 Rh coating using a post impregnation method. The catalysts were then again calcined. Finally, the catalysts were coated with a solution containing Ba and K acetate, dried and calcined.

The washcoat composition is capable of the effective NO_x storage in lean engine operative conditions for later release and catalysis under

combustion stoichiometry or rich air-to-fuel exhaust conditions. The present washcoat composition advantageously incorporates alkali metal barrier(s), if incorporated as a trapping material, these oxide(s) are preferably at or above stoichiometrically determined levels, to prevent migration of alkali materials
5 away from the washcoat and into the supporting substrate. If employed as a barrier, sufficient alkali metal barrier(s) to substantially seal the supporting substrate from the migrating materials is preferred.

Figures 6 and 7 demonstrate the effectiveness of the coating in preventing alkali material migration into the monolith structure. Figure 6 shows
10 the migration of alkali materials on a NO_x adsorber, into the substrate not using the coating, aged at 900 °C for 16 hours in air and water. Figure 7 shows reduced migration of alkali materials on a NO_x adsorber, using the barrier coating embodiment, following aging at 900 °C for 16 hours in air and water. Comparison of Figures 6 and 7 and Figures 8 and 9 reveal that the barrier
15 coating of Figure 7 and Figure 9 reduces the extent to which mobile alkali materials migrate into the substrate.

These incorporated alkali metal barriers, deposited either in the washcoat process or applied as a layer between the washcoat and the substrate, lock in the alkali materials within the washcoat and/or block the migration from
20 the washcoat and as a result, prevent weakening of the substrate which makes the catalyst sensitive to cracking during high temperature transients. Preferably, employment of the alkali metal barrier(s) produces a ceramic supported NO_x absorber having a durability substantially equivalent to the durability of a ceramic supported three-way-catalyst, at a significantly reduced cost relative to
25 the corresponding NO_x absorber washcoat supported on a metallic or alternative ceramic substrate.

While preferred embodiments have been shown and described, various modifications and substitutions may be made thereto without departing from the spirit and scope of the invention. Accordingly, it is to be understood

that the present invention has been described by way of illustration only, and such illustrations and embodiments as have been disclosed herein are not to be construed as limiting to the claims.

What we claimed is:

CLAIMS

1. An exhaust gas catalyst system, comprising:
a substrate; and
a nitrogen oxide adsorber disposed on said substrate, the nitrogen
oxides adsorber comprising:
5 a porous support;
at least one alkali metal barrier; and
a material loaded on said porous support comprising:
a NO_x oxidation catalyst; and
at least one alkali material.
2. The exhaust gas catalyst system of Claim 1, wherein said
porous support comprises alumina, gamma-alumina, delta-alumina, theta-
alumina, zeolite, zirconia, ceria, magnesium oxide, titania, silica, or mixtures
comprising at least one of the foregoing.
3. The exhaust gas catalyst system of Claim 1, wherein said
NO_x oxidation catalyst is platinum, palladium, rhodium, or mixtures comprising
at least one of the foregoing.
4. The exhaust gas catalyst system of Claim 1, wherein the
alkali material is sodium, potassium, cesium, lithium, rubidium, or mixtures
comprising at least one of the foregoing.
5. The exhaust gas catalyst system of Claim 1, wherein the
alkali metal barrier is a material containing an early transition metal oxide.

6. The exhaust gas catalyst system of Claim 5, wherein the alkali metal barrier is a material selected from the group consisting of zirconia, titania, ferric oxide, cordierite, alpha-alumina, mullite, tin oxide, ceria, manganese oxide, silica, vanadium oxide, chromium oxide, hafnium oxide, molybdenum oxide, tungsten oxide, and mixtures comprising at least one of these materials.

7. The exhaust gas catalyst system of Claim 1, wherein the alkali metal barrier is present in an amount sufficient to substantially inhibit the migration of alkali material out of said nitrogen oxides adsorber.

8. The exhaust gas catalyst system of Claim 7, wherein the alkali metal barrier is loaded on said porous support and present in an amount of up to about 2 g/in³.

9. The exhaust gas catalyst system of Claim 8, wherein the alkali metal barrier is present in an amount up to about 0.35 g/in³.

10. The exhaust gas catalyst system of Claim 9, wherein the alkali metal barrier is present in an amount up to about 0.25 g/in³.

11. The exhaust gas catalyst system of Claim 10, wherein the alkali metal barrier is present in an amount of about 0.05 g/in³ to about 0.20 g/in³.

12. The exhaust gas catalyst system of Claim 7, wherein the alkali metal barrier is a layer disposed between said substrate and said porous support.

13. The exhaust gas catalyst system of Claim 12, wherein said layer comprises an atomic film.

14. The exhaust gas catalyst system of Claim 12, wherein said layer has a thickness of up to about 100 μ .

15. The exhaust gas catalyst system of Claim 12, further comprising additional alkali metal barrier mixed with said material.

16. The exhaust gas catalyst system of Claim 1, further comprising a three-way catalyst component, positioned downstream of the nitrogen oxides adsorber or part of the nitrogen oxides adsorber.

17. A method of reducing alkali material migration from a nitrogen oxides adsorber washcoat to a cordierite substrate, comprising:
depositing an alkali metal barrier layer on a substrate; and
depositing on said alkali metal barrier layer, a nitrogen oxides
5 adsorber composition comprising a NO_x oxidation catalyst and at least one alkali material loaded on a porous support.

18. The method of reducing alkali material migration of Claim 17, wherein said porous support comprises alumina, gamma-alumina, delta-alumina, theta-alumina, zeolite, zirconia, ceria, magnesium oxide, titania, silica, and mixtures comprising at least one of the foregoing porous supports.

19. The method of reducing alkali material migration of Claim 17, wherein said NO_x oxidation catalyst selected from the group consisting of platinum, palladium, rhodium, and mixtures comprising at least one of the foregoing catalysts.

20. The method of reducing alkali material migration of Claim 17, wherein the alkali material is selected from the group consisting of sodium, potassium, cesium, lithium, rubidium, and mixtures comprising at least one of the foregoing alkali materials

21. The method of reducing alkali material migration of Claim 20, wherein the alkali material is further combined with an alkaline earth material selected from the group consisting of barium, strontium, calcium, magnesium, and combinations comprising at least one of the foregoing alkaline
5 earth materials.

22. The method of reducing alkali material migration of Claim 17, wherein the alkali metal barrier is a material containing an early transition metal oxide.

23. The method of reducing alkali material migration of Claim 22, wherein the alkali metal barrier is a material selected from the group consisting of zirconia, titania, ferric oxide, cordierite, alpha-alumina, mullite, tin oxide, ceria, manganese oxide, silica, vanadium oxide, chromium oxide,
5 hafnium oxide, molybdenum oxide, tungsten oxide, and mixtures comprising at least one of these materials.

24. The method of reducing alkali material migration of Claim 17, wherein the alkali metal barrier is present in an amount sufficient to substantially inhibit the migration of alkali materials out of said nitrogen oxides adsorber.

25. The method of reducing alkali material migration of Claim 24, wherein the alkali metal barrier is present in an amount of up to about 2 g/in³.

26. The method of reducing alkali material migration of Claim 25, wherein the alkali metal barrier is present in an amount up to about 0.35 g/in³.

27. The method of reducing alkali material migration of Claim 26, wherein the alkali metal barrier is present in an amount up to about 0.25 g/in³.

28. The method of reducing alkali material migration of Claim 27, wherein the alkali metal barrier is present in an amount of about 0.05 g/in³ to about 0.20 g/in³.

29. A method of reducing alkali material migration from a nitrogen oxides adsorber washcoat to a substrate, comprising:
depositing on a substrate, a nitrogen oxides adsorber composition comprising a material loaded on a porous support, the material comprising: a
5 NO_x oxidation catalyst; at least one alkali material; and at least one alkali metal barrier.

30. The method of reducing alkali material migration of Claim 29, wherein said porous support comprises alumina, gamma-alumina, zeolite, zirconia, ceria, magnesium oxide, titania, silica, or mixtures thereof.

31. The method of reducing alkali material migration of Claim 30, wherein said NO_x oxidation catalyst is platinum, palladium, rhodium, or mixtures thereof.

32. The method of reducing alkali material migration of Claim 31, wherein the alkali material is sodium, potassium, cesium, rubidium, or mixtures thereof.

34. The method of reducing alkali material migration of claims 30, wherein the alkali metal barrier is a material containing an early transition metal oxide.

35. The method of reducing alkali material migration of claim 34, wherein the alkali metal barrier is a material containing zirconia (ZrO_2), titania (TiO_2), ferric oxide (Fe_2O_3), cordierite, mullite, tin oxide (SnO_2), zirconia rich oxide with ceria oxide, manganese oxide (MnO_2), silica (SiO_2),
5 vanadium oxide (V_2O_5), chromium oxide (Cr_2O_3), hafnium oxide (HfO_2), molybdenum oxide (MoO_3), tungsten oxide (WO_3), or mixtures thereof, including alkali metal barriers supported on alumina.

36. The method of reducing alkali material migration of Claim 29, wherein the alkali metal barrier is present in an amount sufficient to substantially inhibit the migration of alkali materials out of said nitrogen oxides adsorber.

37. The method of reducing alkali material migration of Claim 36, wherein the alkali metal barrier is present in an amount up to about 0.25 g/in^3 .

38. The method of reducing alkali material migration of Claim 37, wherein the alkali metal barrier is present in an amount of about 0.05 g/in^3 to about 0.20 g/in^3 .




Figure 1.




Figure 2.





Figure 3.



K scavenger in barrier

K scavenger in WC

Figure 5

Figure 4




Figure 7

Figure 6




Figure 9




Figure 8

INTERNATIONAL SEARCH REPORT

International Application No

PC/US 01/02840

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B01D53/94 B01J23/58 B01J37/02 F01N3/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B01D F01N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
E	EP 1 078 678 A (MITSUBISHI MOTORS CORP) 28 February 2001 (2001-02-28) column 1, line 14 -column 2, line 8; claims; figures	1-7, 12, 15, 17, 29
X	DE 197 13 432 A (MAZDA MOTOR ;TOKYO ROKI KK (JP)) 2 October 1997 (1997-10-02) page 2 page 4, line 13-25	1-3, 5-7, 17, 29
X	EP 0 407 915 A (MAZDA MOTOR) 16 January 1991 (1991-01-16) column 2, line 50 -column 3, line 11; claims 1,6; figure 2	1, 3, 5-7, 12, 15, 17, 29



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

14 January 2002

Date of mailing of the international search report

21/01/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Polesak, H

INTERNATIONAL SEARCH REPORT

International Application No

PCI/US 01/02840

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 874 057 A (FARRAUTO ROBERT J ET AL) 23 February 1999 (1999-02-23) column 6, line 17 -column 9, line 67; figures 1A,1B ----	1,17,29
A	EP 0 801 972 A (HONDA MOTOR CO LTD) 22 October 1997 (1997-10-22) ----	
A	EP 0 982 066 A (DEGUSSA) 1 March 2000 (2000-03-01) ----	
A	EP 0 778 072 A (FORD WERKE AG ;FORD FRANCE (FR); FORD MOTOR CO (GB)) 11 June 1997 (1997-06-11) -----	

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 01/02840

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 1078678	A	28-02-2001	JP	2001129402 A	15-05-2001
			JP	2001179098 A	03-07-2001
			EP	1078678 A2	28-02-2001
DE 19713432	A	02-10-1997	JP	9262471 A	07-10-1997
			DE	19713432 A1	02-10-1997
			US	6180558 B1	30-01-2001
EP 0407915	A	16-01-1991	DE	69009601 D1	14-07-1994
			DE	69009601 T2	22-09-1994
			EP	0407915 A2	16-01-1991
			US	5075275 A	24-12-1991
			JP	3207446 A	10-09-1991
US 5874057	A	23-02-1999	AU	5422696 A	10-02-1997
			BR	9609750 A	30-03-1999
			CA	2226412 A1	30-01-1997
			CN	1190909 A	19-08-1998
			EP	0850102 A1	01-07-1998
			JP	11508821 T	03-08-1999
			WO	9702886 A1	30-01-1997
			ZA	9603196 A	04-11-1996
EP 0801972	A	22-10-1997	JP	9276703 A	28-10-1997
			EP	0801972 A1	22-10-1997
EP 0982066	A	01-03-2000	DE	19838282 A1	02-03-2000
			AU	4466799 A	09-03-2000
			BR	9903875 A	31-10-2000
			CN	1263789 A	23-08-2000
			EP	0982066 A1	01-03-2000
			JP	2000084405 A	28-03-2000
			PL	335071 A1	28-02-2000
			TR	9902000 A2	21-04-2000
EP 0778072	A	11-06-1997	US	5727385 A	17-03-1998
			EP	0778072 A2	11-06-1997
			JP	9155200 A	17-06-1997